

Glass Type/Application Borosilicate glass 3.3 acc. to ISO 3585, chemically highly resistant, highly resistant to thermal shock
Special applications in the pharmaceutical industry

Physical Data

Coefficient of mean linear thermal expansion
 $\alpha(20^{\circ}\text{C}; 300^{\circ}\text{C})$ acc. to ISO 7991 $3.3 \cdot 10^{-6}\text{K}^{-1}$

Transformation Temperature T_g 525°C

Glass temperature at viscosity η in $\text{dPa} \cdot \text{s}$

10^{13} (annealing point)..... 560°C

$10^{7.6}$ (softening point) 825°C

10^4 (working point) 1260°C

Density ρ at 25°C $2.23 \text{ g} \cdot \text{cm}^{-3}$

Chemical Data

Hydrolytic resistance

acc. to ISO 719 Class HGB 1

acc. to Ph. Eur. Type I

acc. to USP..... Type I

acc. to JP..... fulfilled

Acid resistance (DIN 12116) Class S 1

Alkali resistance (ISO 695) Class A 2

ASTM E 438 Type I Class A

Chemical Composition
(main components in approx. weight %)

SiO ₂	B ₂ O ₃	Al ₂ O ₃	Na ₂ O	K ₂ O
81	13	2	3.5	0.5

Transmission

